

PRODUCT SERIES:

B90 SERIES BMC

PRODUCT DESCRIPTION:

CORROSION RESISTANT GRADE

Properties	Glass Content 8%		Glass Content 15%	
	Imperial	SI	Imperial	SI
Impact Strength-Izod Notched Test Method: ASTM D-256	7.0 ft.lb./in.	373 J/m	10.0 ft.lb./in.	533 J/m
Impact Strength-Izod Unnotched Test Method: ASTM D-4812	10.0 ft.lb./in.	533 J/m	12.0 ft.lb./in.	640 J/m
Flexural Strength Test Method: ASTM D-790	10,000 psi	69 MPa	12,000 psi	83 MPa
Tensile Strength Test Method: ASTM D-638	4,000 psi	28 MPa	5,000 psi	34 MPa
Compressive Strength Test Method: ASTM D-695	14,000 psi	96 MPa	16,000 psi	110 MPa
Water Absorption (24 Hrs @ 23C) Test Method: ASTM D-570	0.1 to 0.3%	0.1 to 0.3%	0.1 to 0.3%	0.1 to 0.3%
Barcol Hardness Test Method: ASTM D-2583	30 to 60	30 to 60	30 to 60	30 to 60
Heat Distortion Temp @ 264 psi Test Method: ASTM D-648	>400 F	>204 C	>400 F	>204 C
Specific Gravity (+/- .03) Test Method: ASTM D-792	1.5 to 2.0	1.5 to 2.0	1.5 to 2.0	1.5 to 2.0
Shrinkage Test Method: ASTM D-955	0 to 0.2%	0 to 0.2%	0 to 0.2%	0 to 0.2%
Flammability (Average Burn Rate) Test Method: ASTM D-635	0.31 in./min.	.80 cm /min.	.047 in./min.	1.2 cm/min.

The information on this sheet is a guide. The stated values reflect an average of several tests conducted on CI's goods. These values were obtained under ideal conditions and may not be replicated in any particular test, part, or application. Because the values achieved in actual parts depend considerably on part design, molding conditions, and testing methods, no guarantee is made or implied regarding values to be obtained in any specific test, part, or application. CI makes no warranty or representation as to the suitability of any of its goods for use in any application. CI relies on customer to conduct its own tests and judge for itself the suitability of CI's goods.

10/2013

www.idicomposites.com

North America
Noblesville, IN

Europe
Vineuil, France

United Kingdom
Oldbury, UK

Asia/Pacific
Shanghai, China

Caribbean & South America
Aguirre, Puerto Rico

Mexico
Mexico City, Mexico